



# Testa protokols

## Pasūtījums PD6\_izklausanas

**Serijs:** S2

**Tests:** Fiber concrete EN 14651, flexural

Izgatavosanas datums: 25.11.2020 08:40

**Standarts:** EN 14651:2005

Parauga vecums: 54 05:02

**Paraugs:** Prism 150x150x600

Testa datums: 18.01.2021 13:42

Testus veica: A. Dandens

Pasūtītājs U. Skadinš

Name	w [mm]	hsp [mm]	x [mm]	y [mm]	l [mm]	v [mm/min]	f <sub>ct,L</sub> [MPa]	f <sub>R,1</sub> [MPa]	f <sub>R,2</sub> [MPa]	f <sub>R,3</sub> [MPa]	f <sub>R,4</sub> [MPa]
1	154,0	123,8	4,0	5,0	500,0	0,200	4,4	4,5	5,3	5,3	5,1
	Fiber orientation:										
2	154,2	124,0	4,0	5,0	500,0	0,200	4,4	3,0	3,4	3,5	3,5
	Fiber orientation:										
3	153,5	123,1	4,0	5,0	500,0	0,200	4,6	2,4	2,6	2,6	...
	Fiber orientation:										
4	151,9	123,7	4,0	5,0	500,0	0,200	4,3	3,4	3,7	3,7	3,6
	Fiber orientation:										
5	152,4	123,9	4,0	5,0	500,0	0,200	4,5	3,7	4,3	4,4	...
	Fiber orientation:										
6	154,0	124,3	4,0	5,0	500,0	0,200	4,3	3,0	3,3	3,2	3,1
	Fiber orientation:										
7	151,3	123,5	4,0	5,0	500,0	0,200	5,1	5,3	5,6	5,8	5,3
	Fiber orientation:										
8	154,0	123,7	4,0	5,0	500,0	0,200	4,3	3,0	3,5	3,6	3,5
	Fiber orientation:										
9	154,0	123,7	4,0	5,0	500,0	0,200	4,5	3,6	3,8	3,6	3,5
	Fiber orientation:										
10	153,9	123,4	4,0	5,0	500,0	0,200	4,3	3,0	3,3	3,4	3,4
	Fiber orientation:										
11	154,2	123,3	4,0	5,0	500,0	0,200	4,6	2,9	3,1	3,1	3,0
	Fiber orientation:										

